

Product Datasheet / Edition 01/18 / Replaces Edition 08/11 12.01.2018/Bea

Characteristics:

Application	FOAM-X® is a board for short-term indoor use and suitable for decorative applications.				
Sheet construction	Sandwich element with PUR rigid foam core and coated white multiple layer paper.				
Behaviour in external conditions	The board is not flame retardant. The foam shows no water absorption, only the cut cells. The layer is not resistant against water/humidity.				
Chemical effects	The foam is resistant against nearly all solvents and glues. For glues with toluol please make trials. The layers can be processed with standard glues and inks.				
Behaviour against thermal effects	Sheet processing temperature Continuous Td = -20°C up to 100°C Short-term Tk = up to 160°C				
Additional compliance to following standards	DIN ISO 9001:2008 DIN ISO 14001:2004 BS OHSAS 18001:2007 (Development, manufacturing and sales of lightweight boards and PUR-forming parts)				

For more information please see www.display.3AComposites.com All data are based on our current knowledge and experience. They are considered as a reference without being legally binding.



3A Composites GmbH Kiefernweg 10 49090 Osnabrück, Germany

display.eu@3AComposites.com COMPOSITES www.display.3AComposites.com



Product Datasheet / Edition 01/18 / Replaces Edition 08/11 12.01.2018/Bea

Technical Data:

Attribute		Value		Tolerance	Unit	Method
Thickness	3	5	10	± 0,6	mm	KAPA-Meth.
Density	50	44	42	± 3	kg/m³	KAPA-Meth.
Weight per unit area	510	580	780		g/m²	KAPA-Meth.
Compression strength 10% compression set	~0,1	~0,17	~0,35		N/mm²	DIN 53421
Memory effect 10% compression set	~95	~96	~97		%	DIN 53421
Elastic modulus (E-Modul)	~1,5	~2,8	~5,0		N/mm ²	DIN 53421
Bending strength	~4,0	~2,9	~2,1		N/mm ²	DIN 53423
Closed cell structure		> 95			-	KAPA-Meth.
pH-value	8,8	(acid fr	ee)		-	DIN 53124

For available sizes please see delivery programme.

Tolerances:

Width		± 1 mm
Longth	< 2400	±1mm
Length	> 2400	- 1 + 10 mm
Right angle		± 1 mm / m

For more information please see www.display.3AComposites.com All data are based on our current knowledge and experience. They are considered as a reference without being legally binding.



3A Composites GmbH Kiefernweg 10 49090 Osnabrück, Germany

display.eu@3AComposites.com www.display.3AComposites.com